

## **MINERAL COMMODITIES LTD**

ABN 39 008 478 653

Email: <a href="mailto:info@mncom.com.au">info@mncom.com.au</a>
Web: www.mncom.com.au



## **PRODUCT SPECIFICATION SHEET**

## **GRAPHITE CONCENTRATE – SKALAND MEDIUM**

+ 150 mesh (Minimum of 80% retained on 150 mesh i.e. 100 microns)
Minimum 92%, 94%, 95%, 96% Carbon content by LOI
+1592, +1594, +1595, + 1596
0.5% Max

Typical Particle Size Distribution (PSD) Shown below: -

Typical Particle Size Distribution (PSD)	
Size Fraction	Weight % Retained
+250	2.6
+212	10.1
+180	16.4
+150	28.7
+100	28.5
-100	13.6

Typical Particle Size Distribution (PSD):

Note: the commodity is a natural material with some variability around the typical PSD